

IN THE CLAIMS

Please cancel Claims 22 and 23.

Please amend the claims as shown in the attached marked-up copy to read as follows:

10. (Amended) The process as claimed in claim 9, wherein a support is employed which does not adversely affect the alignment of the cholesteric layer cast thereon during drying and curing.
11. (Amended) The process as claimed in claim 9, wherein the support has an adhesive strength of less than about 1 cN to the dried and crosslinked first cholesteric layer cast thereon.
12. (Amended) The process as claimed in claim 9, wherein a layered material comprising a plurality of cholesteric layers is produced, where the second layer can be removed selectively from the first layer on the support as a composite with any further layers.
13. (Amended) The process as claimed in claim 9, wherein the support is selected from the group consisting of a plastic support, a metal support, a glass support, and a ceramic support [supports].
14. (Amended) The process as claimed in claim 13, wherein the plastic support comprises a release layer of crosslinked, optionally aligned, cholesteric material onto which the first cholesteric layer is cast.
15. (Amended) The process as claimed in claim 14, wherein the adhesion between the plastic support and the release layer is at least about twice the adhesion between release layer and first cholesteric layer.
16. (Amended) The process as claimed in claim 9, wherein the coating compositions for the cholesteric layer(s) and the release layer independently of one another have a viscosity

17. (Amended) The process as claimed in claim 9, wherein the crosslinking of the cholesteric layer(s) and of any cholesteric release layer present is carried out by electron beams or UV radiation with simultaneous warming of the layer 25 to be cured, where the emitter power is in the range from about 50 to 200 watts/cm.

18. (Amended) The process as claimed in claim 17, wherein the layer temperature during the radiation curing is at least 60°C.

19. (Amended) The process as claimed in claim 9, wherein a further support film is applied to the cholesteric layer applied last, and the one or more cholesteric layer(s) is (are) removed from the support as a composite.

20. (Amended) The process as claimed in claim 9, wherein one or more cholesteric layer(s) is (are) removed from the support by blasting with compressed air, a water jet, steam or with the aid of a knife coater and ground to give pigments.

21. (Amended) A composition comprising at least one cholesteric pigment as claimed in claim 8 and one or more additional components.

24. (Amended) A polarizer comprising a layered material as claimed in claim 1, which is, optionally, applied to a support film.

25. (Amended) A broad-band polarizer comprising a layered material as claimed in claim 1 having a number of from 3 to 20 cholesteric layers with reflection maxima matched to one another, where the polarizer has a total thickness without support film in the range from about 2 to 50 μm .

Please add the following claims:

26. (New) The cholesteric layered material as claimed in claim 4, wherein the

27. (New) The cholesteric layered material as claimed in claim 4, wherein the cholesteric layer has a mean dry layer thickness of less than or equal to about 1 μm .

28. (New) The process as claimed in claim 18, wherein the layer temperature during radiation curing is at least 80°C.

29. (New) The process as claimed in claim 18, wherein the layer temperature during radiation curing is at least 90°C.

30. (New) A method of making an article comprising incorporating the cholesteric layered material as claimed in claim 1 into and/or onto the article.

31. (New) The method as claimed in claim 30, wherein the article is selected from the group consisting of a motor vehicle, a motor vehicle accessory, a computer, a leisure article, a sport article, a toy article, an optical article, a cosmetic article, a textile article, a leather article, a jewelry article, a writing article, a spectacle frame, a construction article, a print article, and a paint article.

32. (New) The method as claimed in claim 31, wherein the article is a motor vehicle and the cholesteric layered material is painted onto the motor vehicle.

33. (New) A method of making an article comprising incorporating the composition as claimed in claim 8 into and/or onto the article.

34. (New) The method as claimed in claim 32, wherein the article is selected from the group consisting of a motor vehicle, a motor vehicle accessory, a computer, a leisure article, a sport article, a toy article, an optical article, a cosmetic article, a textile article, a leather article, a jewelry article, a writing article, a spectacle frame, a construction article, a print article, and a paint article.

35. (New) The method as claimed in claim 34, wherein the article is a motor vehicle